

# PUMA-CRETE HF®

## Heavy Duty Polyurethane Mortar Flooring

### Technical Datasheet



#### DESCRIPTION

Puma-Crete HFB® is a heavy duty floor with matte finish, available in smooth or orange peel texture. It is a low odor, urethane based, screeded floor, designed to provide excellent resistances to abrasion, chemical attack and other physical aggression, and is designed for industrial facilities utilizing forklifts and other types of heavy loads with commonly used rubber wheels.

#### COMPOSITION

Water dispersed polyurethane resin system combined with graded silica aggregates, and optional 2-part polymer topcoat.

#### APPEARANCE

Matte finish. Texture may be specified as: LIGHT, MEDIUM or HEAVY. Note: heavy texture requires brush cleaning or high pressure water.

#### DURABILITY

Resistant to impact, abrasion, and heavy loading from forklifts, pallet jacks and carts, commonly found in industrial facilities.

#### WATER AND MOISTURE TOLERANCE

Handles up to 15 lbs of water vapor transmission and over 99% concrete internal RH. The flooring functions as a vapor permeable, mitigation system.

#### CERTIFICATIONS

Puma-Crete HF is accepted by USDA, FDA, SQF, HACCP, BRC, and many other agencies

#### THICKNESS

Typical 6mm (1/4") to 8mm (3/8").

#### TYPICAL APPLICATIONS

Industrial Manufacturing and Processing Facilities

#### SUBSTRATES

Concrete, structurally sound toppings including ceramic, quarry tile and brick, polymer reinforced screeds, grano concrete. Other structurally sound substrates may be suitable, based upon results of custom laboratory testing of the materials, for suitable adhesion. Fiberglass reinforcement of substrate may be required, for some customized applications.

#### SURFACE PREPARATION

To be assured of maximum adhesion and properties from EP Floors resin products the correct surface preparation is essential. Please refer to technical data sheet "Surface Preparation". In order to ensure the finished system remains fully bonded to the sub-floor, it is recommended that the floor perimeter is saw cut and keyed-in 1/2" deep into the substrate, to produce a structurally durable edge. This shall run along all terminations of the new flooring, which are not adjacent to vertical surfaces (e.g.- doorways, edges, drains, cleanouts).

#### APPLICATION CONDITIONS

(60-86° F) Ideal working temperature is 70 deg° F

#### APPLICATION

**Puma-Crete HF** - one pass, urethane mortar.  
(applied 1/4-3/8 inch thickness)

#### COVERAGE RATES

(1/4 inch) one unit = 2.25m<sup>2</sup> (22 ft<sup>2</sup>) at 6mm  
(1/2 inch) one unit = 1.10m<sup>2</sup> (11 ft<sup>2</sup>) at 12mm

#### SPECIFICATION DETAIL

Please refer to Engineering/Architectural Details.

#### MAINTENANCE (see Puma-Crete Cleaning Instructions)

Regular cleaning of the applied system is recommended in order to maintain slip resistant properties and cosmetics. Normal proprietary cleaning agents w/ standard auto floor scrubber. Washing/steam cleaning may be employed, if needed.

#### CURE SCHEDULE (70 deg F)

Puma-Crete HF®: 12 hours foot traffic, 24 hrs full cure \*

Puma-Crete TF: 18 hours foot traffic, 36 hrs full cure \*

\*catalyst available for faster curing, if faster cure time required.

#### CHEMICAL RESISTANCE

Excellent resistances to organic and inorganic acids, alkalis, fuel and hydraulic oils, aromatic and aliphatic solvents. Please refer to Puma-Crete HFB® chemical resistance guide.

#### COLORS AVAILABLE

Standard colors are: *Red and Steel Gray*

Premium colors are available (see color chart).

#### TECHNICAL DATA

Compressive strength: ASTM C579 9,620 psi

Tensile strength: ASTM C307 4,900 psi

Flexural strength: ASTM D790 10,200 psi

Shear Strength: ASTM D732 5,100 psi

Abrasion resistance ASTM C779 (method A) .019 in @ 60 min

#### HEALTH AND SAFETY

This is a water based and 0 gram VOC/Liter product system. Please read the material safety data sheets, for further detailed information on safe handling and use of this product.

#### STORAGE, MIXING & APPLICATION

The storage, mixing and application conditions can affect the quality of the finish produced. Materials are freezable, and therefore must be stored above 35 deg F. Optimum application temperature is 70 deg F.

#### TECHNICAL ADVICE

For further information on this or any other Puma-Crete product, please contact our Customer Care Department on (800) 808-7773 USA. Outside USA: 1-413-283-5164



ENGINEERED TO EXCEL!  
1-800-808-7773

[www.EPFloors.com](http://www.EPFloors.com)

BOSTON - BALTIMORE - ATLANTA - CHICAGO - DALLAS - DENVER - LOS ANGELES